

Technical Leaflet

WorléeThix A 2126

Art.-No. 112005-15918

Revision: 16.11.2020

WorléeThix A 2126 is a thixotropic, isocyanate cross-linkable acrylic resin.

Technical Data:

Non volatile content, 1h/125 °C, DIN EN ISO 3251	60% ± 2
Hydroxyl content, on solids	approx. 2,6%
Delivery form	60% in butyl acetate

Application and Properties:

WorléeThix A 2126 can be cross-linked with with aliphatic and aromatic polyisocyanates to formulate air and forced drying systems for metal, wood and plastics. The aliphatic system shows excellent hardness, good chemical resistance and a good outdoor durability already at room temperature.

Recommended Storage and Transport Conditions:

Protect from sunlight and temperatures above 30 °C.

Shelf Life:

The storage stability of WorléeThix A 2126 in the originally closed barrel is at a storage temperature from +5 to +25 °C six months, counted from the day of the delivery ex works.