

Preliminary Technical Leaflet

WorléeCryl 7186 MF

Art. No. 212054-22270

Revision: 10.01.2019

Hard methacrylic copolymer emulsion.

Technical Data:

Non volatile content, DIN EN ISO 3251	46% ± 1
pH - value, DIN ISO 976	8 - 9
Viscosity, 20 °C, Brookfield, DIN EN ISO 2555	max. 500 mPa·s
Emulsion system	anionic
MFFT Minimum film forming temperature ISO 2115	56 °C
Delivery form	46% in water

Outstanding Characteristics:

Very hard polymer improving the surface properties in water soluble lacquer systems.

Excellent compatibility with other polymer emulsions.

Properties and Application:

As combining agent W'Cryl 7186 MF effects improving in film hardness, sanding, blocking resistance and stackability.

The storage stability in the originally closed barrel is at a storage temperature from + 5 to + 25 °C six months, counted from the day of the delivery ex works.

The product described in this preliminary technical data sheet is a trial product which has not yet been industrially manufactured. Worlée-Chemie GmbH has not yet been able to monitor performance over a sufficiently long period and therefore, cannot accept liability or provide a warranty for the product, in particular on its suitability for specific applications.